



Fenomen Exterior Primer

PRODUCT DESCRIPTION

An acrylic copolymer emulsion based, high hiding, adherence and penetration power, top coat exterior wall primer

SPECIFICATIONS

Establishes a binding bridge between the paint and the surface, increases adherence, reduces paint consumption. Allows the moisture inside the structure to escape thanks to its high permeability feature. Prevents the paint to be applied thereon from being absorbed unequally by the surface.

SURFACES TO BE APPLIED

It can be applied to plaster, screed plaster, bush-hammered concrete, concrete, grinded concrete, exposed concrete, betopan, MDF, OSB, mineral-based top coat decorative coatings, top coat silicone decorative coatings, and faded but still self-supporting old painted, ready-plaster surfaces.

APPLICATION

The surface to be applied needs to be firm, dry, clean, and self-supporting. If any, all kinds of dirt, dust, mold oil, and loose plaster layers should be removed. On concrete, exposed concrete, and newly plastered surfaces, the setting time should be waited for (28 days), and loose plaster particles should be cleaned from the surface by scraping or similar methods. If necessary, surface corrections and repairs should be performed. It is not recommended to apply between 10:00 and 16:00 in hot weather. It is advised to apply on shaded facades. During the application and drying period of the product, the ambient and surface temperatures should be between +5°C and +30°C, and it should be protected from all kinds of precipitation, dew, and frost. Our products should be applied to the infrastructure surfaces created in accordance with the General Technical Specification for Construction dated June 30, 2007 and numbered 26568.

WARNINGS

Plaster-applicable surfaces:

When painting cement-based surfaces for the first time, Fawori Exterior Plaster should be added with a mixture of fresh white or gray cement and water (boza consistency), up to 20% of its weight. Applying the prepared mixture directly to freshly cleaned and moistened plaster or concrete surfaces is recommended. Prior to applying putty to previously painted surfaces, the exterior paint primer should first be applied. Afterwards, ready-made putty is applied straight away without being mixed with cement. Ready-to-use putties should be applied with a maximum thickness of 1 mm to prevent cracking and collapse.

For grading and smoothing of 1–10 mm, Fawori T1 should be used. It is advised to make a repair mortar with a mixture of 1 kg of latex and 4 kg of water when making 25 kg of fawori T1.

The reinforcement mesh should be applied by making 10 cm overlaps at the joints along the entire surface if the crack application proceeds along a line and there are cracks that are 10 cm wide along that line. Reinforcement mesh should be applied as close to the outer surface as 1/3 of the total thickness of the surface smoothing and grading material to be applied.



Particularly between the application of cement-based surface smoothing and repair pastes and the final coat of paint, the surfaces should be shielded from excessive dew and precipitation. Otherwise, white specks will appear on the surface. In such an image, the surface should be moistened with a car wash brush and 1 part Filox 451 + 1 part Water mixture should be applied to the surface.

Airless Spraying

Pressure : 140bar
Nozzle Angle : 50°
Nozzle Size (inch) : 0.013"
Thinning : %5

THINNING

It should be thinned with clean water by 10% in applications made with a brush or roller, and by a maximum of 5% in applications made by spraying.

DRY TIME (at 20°C, 65% HR)

Primer drying: 6-8 hours

CONSUMPTION

Depending on the type, absorbency, and structure of the surface to be applied, an area of 5–8 m² can be primed with 1 Kilogram in one coat. A controlled sample study should be performed for final consumption.

STORAGE

It can be stored for 3 years in its unopened container in a cool, dry place, protected from frost and direct sunlight. You should close the lid of the container immediately after use in an airtight manner.

CONTAINER

20 Kg, 3,5 Kg

WARNING WORD

Caution

HAZARD STATEMENT

H317: Causes allergic skin reactions

PRECAUTIONARY STATEMENT

P101: If medical advice is required, have the product container or label at hand.

P102: Keep out of reach of children.

P103: Read label before use.

P261: Avoid breathing dust/fume/gas/mist/vapors/spray.

P280: Wear protective gloves/protective clothing/eye protection/face protection

P333+P313: If skin irritation or rash occurs: Get medical advice/attention

P501: Dispose of the contents/container in accordance with local/regional/national/international legislation.

**Item No**

15.540.1324, 15.540.1325, 15.540.1329, 15.340.1337, 15.340.1338,
15.340.1339

Market No

10.300.1172

Since this technical sheet is prepared on the basis of laboratory data under normal conditions, consult the technical personnel for any details that are not sufficiently addressed above. Otherwise, errors that may arise as a result of a lack of information do not impose any responsibility on the manufacturer. The right to change this information is reserved by our company.

This product is manufactured by Betek AŞ, which has the certificate of conformity with TS EN ISO 9001, TS EN ISO 14001, TS ISO 45001, TS EN ISO 50001, TS ISO 10002, TS EN ISO/IEC 27001 standards.