



# Silicone Exterior FacadePaint

## PRODUCT DESCRIPTION

Silicone, acrylic copolymer emulsion-based, matte, exterior facade top-coat paint.

## SPECIFICATIONS

- ✓ Contains silicone
- ✓ Matte
- ✓ Vivid color options
- ✓ High level of water repelling
- ✓ Breathable
- ✓ 5-year UV-resistance guarantee
- ✓ Resistant to friction and impacts

Holds on to the application surface well thanks to its superior adherence power. Resistant to atmospheric conditions, air pollution, and solar rays. Enables the moisture on the surface to be released thanks to its breathability. Easy to apply, spreads easily over the surface.

## APPLICATION SURFACES

Can be applied to plaster, rough plaster, comb mosaic, polished mosaic, concrete, brute concrete, concrete board, MDF, OSB, and even to old painted ready-plaster type surfaces that can still support themselves even though they may have lost their color.

## APPLICATION

Ensure the application surface is firm, dry, clean and self-supporting. Remove all types of stain, dust, block grease and loose layers. Observe the setting period (28 days) on concrete, brute concrete, new plastered surfaces, and clean the loose plaster particles with scraper or similar methods. Correct and repair the surface if required. Begin painting after applying the appropriate primer. Avoid application between 10 AM and 04 PM during hot weather conditions. Recommended to be applied to shady walls. Ensure the ambient and surface temperatures are between +5°C and +30°C, and protect the surface from all kinds of precipitation, dew and frost.

Our products should be applied on substructure surfaces that are built in line with 30.06.2007 dated General Construction Specifications No. 26568.

## WARNINGS

For cement-based surfaces that will be painted for the first time, mix Fawori Exterior Paste with fresh white/gray cement and a water mixture that is equal to 20% of its weight. Apply the mixture directly on cleaned and moisturized plaster/concrete surfaces. If a plaster application will be applied on old painted surfaces, heavy scoring must be applied to reach the raw plastered surface. Ensure that the ready-to-use pastes are applied with a maximum thickness of 1 mm in order to prevent cracking and slumping.

Apply Stako 0 for a 0-3 mm surface for leveling and correcting. Recommended to use 1 kg of Lateks + 4 kg of water for thinning.

Apply Stako for a 3-10 mm surface for leveling and correcting. Recommended to use 1 kg of Lateks + 4 kg of water for thinning.

Apply Stako Plus for a 5-40 mm surface for leveling and correcting. Recommended to use 1 kg of Lateks + 4 kg of water for thinning.

## BETEK BOYA VE KİMYA SAN. A.Ş.



Apply glass-fiber mesh with 10 cm width along the crack if the crack continues as a straight line and with 10 cm at all joints throughout the surface if there are numerous cracks. Ensure the glass-fiber mesh is applied as close to the exterior surface as 1/3 of the total thickness of the surface correction and leveling material.

Protect the surfaces from extreme dew and rain especially during the period from the cement-based surface correction / repair paste application to the final coat application. Otherwise, there will be efflorescence. In such a case, moisten the surface with a car wash brush and apply 1 unit of Disboxan 451 + 1 unit of water mixture.

#### **For airless spraying:**

Pressure: 140 bar

Nozzle Angle: 50°C

Nozzle Size (inch): 0.019"-0.021"

Thinning: 5%

#### **THINNING**

Thin by max. 15% with clean water in applications with brush and roller, and by max. 5% with clean water in spraying. Ensure all products are thinned at the same rate in order to prevent color tone differences.

#### **DRYING TIME (at 20°C, 65% RH)**

Touch dry: 1-2 hours

Dry period between the primer and the coats : 6-8 hours

Final-dry : 24 hours

#### **CONSUMPTION**

Depending on the type, absorbency and structure of the surface to be applied, an area of 7-10 m<sup>2</sup> can be painted with 1 liter in a single layer. Perform a controlled sample run to estimate the precise consumption amount.

#### **STORAGE**

It can be stored in its unopened package for 3 years, in a cool and dry place, away from frost and direct sunlight. Close the lid air-tight immediately after application..

#### **PACKAGE**

15 L, 7.5 L, 2.5 L

#### **WARNING STATEMENT**

Caution

#### **HAZARD STATEMENT**

H317 May cause an allergic skin reaction.

#### **PRECAUTIONARY STATEMENTS**

P101 If medical advice is needed, have the product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P261 Avoid breathing its dust/fume/gas/mist/vapors/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P333+P313: If skin irritation or a rash occurs: Get medical advice/attention.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.



Protect the surfaces from extreme dew and rain especially during the period from the cement-based surface correction / repair paste application to the final coat application. Otherwise, there will be efflorescence. In such a case, moisten the surface with a car wash brush and apply 1 unit of Disboxan 451 + 1 unit of water mixture.

**For airless spraying:**

Pressure: 140 bar

Nozzle Angle: 50°C

Nozzle Size (inch): 0.019"-0.021"

Thinning: 5%

**THINNING**

Thin by max. 15% with clean water in applications with brush and roller, and by max. 5% with clean water in spraying. Ensure all products are thinned at the same rate in order to prevent color tone differences.

**DRYING TIME (at 20°C, 65% RH)**

Touch dry: 1-2 hours

Dry period between the primer and the coats: 6-8 hours

Final-dry : 24 hours

**CONSUMPTION**

Depending on the type, absorbency and structure of the surface to be applied, an area of 7-10 m<sup>2</sup> can be painted with 1 liter in a single layer. Perform a controlled sample run to estimate the precise consumption amount.

**STORAGE**

It can be stored in its unopened package for 3 years, in a cool and dry place, away from frost and direct sunlight. Close the lid air-tight immediately after application..

**PACKAGE**

15 L, 7.5 L, 2.5 L

**WARNING STATEMENT**

Caution

**HAZARD STATEMENT**

H317 May cause an allergic skin reaction.

**PRECAUTIONARY STATEMENTS**

P101 If medical advice is needed, have the product container or label at hand.

P102 Keep out of reach of children.

P103 Read label before use.

P261 Avoid breathing dust/fume/gas/mist/vapors/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P333+P313: If skin irritation or a rash occurs: Get medical advice/attention.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.



Conforms to TS 7847.



Conforms to the G communiqué.

TSE

Silicone Exterior FacadePaint	1
PRODUCT DESCRIPTION	1
SPECIFICATIONS	1
APPLICATION SURFACES	1
APPLICATION	1
WARNINGS	1
For airless spraying:	2
THINNING	2
DRYING TIME (at 20°C, 65% RH)	2
CONSUMPTION	2
STORAGE	2
PACKAGE	2
WARNING STATEMENT	2
HAZARD STATEMENT	2
PRECAUTIONARY STATEMENTS	2
For airless spraying:	3
THINNING	3
DRYING TIME (at 20°C, 65% RH)	3
CONSUMPTION	3
STORAGE	3
PACKAGE	3
WARNING STATEMENT	3
HAZARD STATEMENT	3
PRECAUTIONARY STATEMENTS	3
Conforms to the G communiqué.	4
	4

Pos. No. 5  
This product is manufactured by Betek A.Ş. with certificate of conformity to the standards 5  
Rev4 March 2020 5

**Pos. No.**  
27,560/7

**Rate No**  
04.522/S

This technical sheet is prepared based on laboratory data under normal conditions, consult the technical personnel for details that are not provided above. Otherwise, the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided.

**This product is manufactured by Betek A.Ş. with certificate of conformity to the standards TS ISO / IEC TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.**

**Rev4 March 2020**