



Fenomen Interior Paint

PRODUCT DESCRIPTION

Silicone based, semi-matte, smooth, elastic textured, wipeable, decorative water based interior paint.

SPECIFICATIONS

- ✓ Water-based, silicon-based
- ✓ Semi-matte
- ✓ Smooth
- ✓ Wipeable
- ✓ Stain-repellent, easy-to-clean (stain block technology)
- ✓ Elastomeric, bridging capillary cracks
- ✓ Breathable

Fawori Fenomen Interior Paint, causes no cracking, blistering or flaking if applied in line with building structure standards. No disturbing odor due its water-based formula and it is environmentally-friendly.

APPLICATION SURFACES

Fawori Fenomen Interior Paint is applied after priming on interior old-new painted/plastered ceilings-walls, plaster, putty, plasterboard, concrete board, OSB, glass textile surfaces.

APPLICATION

Ensure that the application surface is smooth, firm and able to bear the primer and top-coat paint. Clean all types of stain, dust, block grease, loose layers and make the required surface corrections. Observe the setting period (28 days) for concrete, exposed concrete and new plastered surfaces.

Previously painted water-solvent based surfaces: Sand the surface using fine grained emery paper before applying primer.

Use Fawori Interior Transformation Primer on the new plastered surfaces that will be painted for the first time.

Fawori Transparent Primer or Fawori Concentrate Primer diluted 1/7 should be applied as a single layer (by making a round with roll upwards and downwards) on absorbing, dusting surfaces such as gypsum, lime, whitewash, aerated concrete without scouring and glazing. Do not apply directly on lime. In order to increase the coverage of the paint on very dirty surfaces, after applying 1 coat of stain-covering paint and priming the surface with Fawori Transparent Primer, apply two layers of topcoat. Ensure the ambient and the surface temperature is between +5°C and +30°C during the application and until the product is fully dry.

WARNING

Recommended to be applied using satin roller on smooth surfaces such as satin plaster or paste, and using plastic roller on primed or absorbent rough surfaces to ensure the desired texture and ease of application.

Transparent Primers: Apply Fawori Concentrated Primer or Fawori Transparent Primer on absorbing interior surfaces and high dust generating surfaces like plaster, lime, whitewash and aerated concrete (interior-exterior) as a single coat without combing and polishing. A glassy surface will be formed when you apply these primers to the old painted (water-solvent painted) surfaces without high dust generation and surfaces with glue / paste. Coverage, cracking and/or adherence issues can be seen on such surfaces even though you apply the top coat 7-8 times. In such a case, continue sanding and scraping until the glassy layer is fully removed.

Pigment Primers: Use Fawori Interior Transformation Primer as primer/transition primer on wall surfaces that are both primed an painted with water-solvent based paints. Since the binder will be absorbed when such primers are applied to the absorbing and high dust generating surfaces like plaster, lime, whitewash and aerated concrete, there will be a dusty appearance and other problems on the surface.



Pasted Surfaces: Apply transparent primers without combing or polishing (by moving the roller upwards just for one turn) on absorbing and high dust generating surfaces like plaster, lime, whitewash and aerated concrete if the wall surfaces will be corrected with a paste. Then apply the ready-to-use paste (the surface must be leveled with a paste that is compatible with bottom and top coat paint), continue with Fawori Pro Primer and move on to the final coat of paint. Notch the surface frequently if plaster is to be applied on the old paint. Otherwise, avoid applying plaster directly on paint If applied, the final paint coat will fall along with the plaster.

Lime and Loose Layer Cleaning: Clean the old paint layers that cannot hold and absorbing surfaces like lime under the paint using a wire brush, scraper and/or spiral. Or clean using a water jet with maximum 250 bar pressure after testing. Do not forget to make a sample test for water jet or sanding methods. Otherwise, high pressure may damage the surfaces and lead to significant repair and correction needs.

For airless spraying:

Pressure: 120-140 bar Nozzle Angle: 50° Nozzle Size (inch): 0.019" Thinning (Water): 5% (by volume)

THINNING

Recommended to be applied in two coats after thinning by 10-15% with clean water in brush and roller applications.

DRYING TIME (at 20°C, 65% RH)

Touch dry: 30-60 minutes Resting period between coats: 4-6 hours Final drying: 24 hours (drying time may increase at higher relative humidity and lower temperature)

CONSUMPTION

Depending on the type, absorbency and structure of the application surface an area of 13-19 m² can be painted in a single coat with 1 Liter. Perform a controlled sample run to estimate the precise consumption amount.

STORAGE

It can be stored in its unopened package for 3 years, in a cool and dry place, away from frost and direct sunlight. Close the lid air-tight immediately after application.

PACKAGE 15 L, 7.5 L, 2.5 L

HAZARD STATEMENT

H317 May cause allergic skin reactions.

PRECAUTIONARY STATEMENTS

P101 If medical advice is needed, keep the product container or label.

P102 Keep out of the reach of children.

P103 Read label before use.

P261 Avoid breathing its dust/fume/gas/mist/vapor/spray.

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P321 Specific treatment required (see label).

P363 Wash contaminated clothing before reuse.

P333+P313 If skin irritation or itching occurs: Get medical advice/attention.

P501 Dispose of contents/container in accordance with local, regional, national and international regulations.



Complies with TS 5808/2012.



Complies with the G communique.

TSE

Wet Scrub Resistance: Class 1 Coverage Strength: Class 2 (7m²/L) Granule Size: Fine Gloss: Semi-matte

Pos. No. 25.043/2A, 25.048/3, 25.048/4, 25.048/4A, 25.043/4A, 25.043/4B, 25.043/4C, 25.048/3A

Rate No. 04.524/02, 04.524/07

This technical sheet is prepared based on laboratory data at normal conditions, consult technical personnel for details that are not provided above. Otherwise the manufacturing company cannot be held responsible for failures that may arise due to lack of knowledge. Our company reserves the right to change the information provided.

Where necessary, please refer to Material Safety Data Sheets for more information on health, safety and handling risks, and precautions associated with the products.

This product is manufactured by Betek A.Ş., with certificate of conformity to the standards TS EN ISO 9001, TS EN ISO 14001, TS 18001, TS EN ISO 50001, TS ISO 10002, TS ISO/IEC 27001.

Rev1 March 2020